





Product card


Wall sandwich panel with visible fastening








Board cross-section



Joining of panels





^{*} Module availability is determined individually with the sales department..

Core	WOOL							
Density [kg/m³]	100 ± 10							
WOOL panel thickness [mm]	80	100	120	160	180	200	220	240
Weight[kg/m²]	16,6	18,6	20,6	24,6	26,6	28,6	30,6	32,6
Effective width [mm]	1150, 1000*							
Total width [mm]	1171, 1021*							
Min. panel length [m]	2,0							
Max. panel length [m]	15,0							
Outer/inner sheet thickness [mm]	0,5-0,7 / 0,5-0,7							
U-value [W/m²K]	0,54	0,43	0,36	0,27	0,24	0,22	0,20	0,18
Fire spread degree	NRO							
Type of external / internal profiling	[M], [T], [R], [F] / [M], [T], [F]							
External / internal corrosion resistance	C1, C2, C3 (C4 ÷ C5) / A1 (A2 ÷ A5)							
Standard coatings	Poliester Interior [INT], Poliester Standard [RAL], HERCULIT [HC], MULTILAYER 40 [MLT]							
Special coatings	PVDF, F	PUR, PVC (I	P), PVC (F)	- FoodSafe	•			
Accessories	fixing system, seals, flashings, rooflight							

Packaging of sandwich panels

Panel thickness [mm]	Modular width [mm]	Number of panels per pack [pcs]	Number of packages on a vehicle [pcs]	Maximum package height[mm]	Package height[mm]	Panel weight [kg/m2]	Weight of 1 package [kg]	Surface area of panels [m2/car]**
80	1150	15	4	1300	2600	17,9	2779,0	621,0
100	1150	12	4	1300	2600	19,9	2471,6	496,8
120	1150	10	4	1300	2600	21,9	2266,7	414,0
160	1150	7	4	1220	2440	25,9	1876,5	289,8
180	1150	6	4	1180	2360	27,9	1732,6	248,4
200	1150	6	4	1300	2600	29,9	1856,8	248,4
220	1150	5	4	1200	2400	31,9	1650,8	207,0
240	1150	5	4	1300	2600	33,9	1754,3	207,0

 $[\]langle \mathbf{i} \rangle$

^{*} Module availability is agreed individually with the sales department.


^{**} Surface area of panels on car calculated for panel lengths of 9 m.




For SPW-S CORE WOOL panels in thicknesses of 120-240 mm, it is possible to mill the core joints in the locks on special request



Board cross-section



Joining of panels





 $^{^{\}star}$ Module availability is determined individually with the sales department..

Core	WOOL						
Density [kg/m³]	100 ± 10						
WOOL panel thickness [mm]	120	160	180	200	220	240	
Weight [kg/m²]	20,6	24,6	26,6	28,6	30,6	32,6	
Effective width [mm]	1150, 1000*						
Total width [mm]	1171, 1021*						
Min. panel length [m]	2,0						
Max. panel length [m]	15,0						
Outer/inner sheet thickness [mm]	0,5-0,7 / 0,5-0,7						
U-value [W/m²K]	0,36	0,27	0,24	0,22	0,20	0,18	
Fire spread degree	NRO						
Type of external / internal profiling	[M], [T], [R], [F] / [M], [T], [F]						
External / internal corrosion resistance	C1, C2, C3 (C4 ÷ C5) / A1 (A2 ÷ A5)						
Standard coatings	Poliester Interior [INT], Poliester Standard [RAL], HERCULIT [HC], MULTILAYER 40 [MLT]						
Special coatings	PVDF, PU	R, PVC (P), P\	/C (F) - FoodS	afe			
Accessories	fixing system, seals, flashings, rooflight						

Packaging of sandwich panels


Panel thickness [mm]	Modular width [mm]	Number of panels per pack [pcs]	Number of packages on a vehicle [pcs]	Maximum package height[mm]	Package height[mm]	Panel weight [kg/m2]	Weight of 1 package [kg]	Surface area of panels [m2/car]**
120	1150	10	4	1300	2600	21,9	2266,7	414,0
160	1150	7	4	1220	2440	25,9	1876,5	289,8
180	1150	6	4	1180	2360	27,9	1732,6	248,4
200	1150	6	4	1300	2600	29,9	1856,8	248,4
220	1150	5	4	1200	2400	31,9	1650,8	207,0
240	1150	5	4	1300	2600	33,9	1754,3	207,0




^{*} Module availability is agreed individually with the sales department.


^{**} Surface area of panels on car calculated for panel lengths of 9 m.

External profiling

















FLAT[F]




Internal and external profiling are available in any configuration.

Internal profiling











FLAT [F]



ATTENTION! Due to the structure of sandwich panels with FLAT [F] profiles, the so-called effect may occur. "waves" of the sheet metal. This is a natural phenomenon for this type of products. We recommend contacting the technical department to choose the optimal solution.

Coatings and colors

POLIESTER Interior [INT] - Available colors for interior cladding



POLIESTER Standard [RAL] - Available colors for exterior cladding



HERCULIT [HC]



MULTILAYER 40 [MLT] - Available colors for exterior cladding





Printing technology does not allow faithful rendering of colors. Therefore the colors shown are indicative and may differ from actual colors.




In addition, on individual order, non-standard colors and coatings are available, outside the palette shown (PVDF, PUR, PVC (P), PVC (F) - FoodSafe).

Coating parameters

Code	Coating thickness	Corrosion resistance	UV resistance
POLIESTER Interior [INT]	15 μm	RA2	Not applicable
POLIESTER Standard [RAL]	25 μm	RC3	RUV2
HERCULIT [HC]	35 μm	RC4	RUV4
MULTILAYER 40 [MLT]	40 μm	RC3	RUV3

Notes







MODULAR SERIES



COMPACT SERIES



CLASSIC SERIES



RETRO SERIES



PANEL SERIES







TRAPEZOIDAL











Wall Sandwich PANELS



SKRIN, LINEA, SINUS









PERFORATION







